

SPECIFICATIONS PRINTED CARPETS

1300 GR SAXONY FR

TECHNICAL DETAILS

Manufacturing process	ISO 2424	Tufting 1/10"		
Construction	ISO 2424	Cut pile - saxony		
Colour	ISO 2424	Chromojet print		
Pile composition		100 % PA		
Primary backing	ISO 2424	PP woven		
Secondary backing	ISO 2424	Felt backing		
Pile weight	ISO 2424	+/-	1.300	g/m ²
Total weight	ISO 8543	+/-	2.600	g/m ²
Pile height	ISO 1766	+/-	6,0	mm
Total thickness	ISO 1765	+/-	10,5	mm
Number of knots	ISO 1763	+/-	237.000	/m ²
Width	ISO 3018	+/-	400	cm

FUNCTIONAL PROPERTIES

Wear classification	EN 1307:2008	CL 33 – heavy contract		
Comfort rating	EN 1307:2008	LC 4		

PHYSICAL PROPERTIES

Surface resistance	ISO 10965:2011	+/-	Ω		
Vertical resistance	ISO 10965:2011	+/-	Ω		
Sound absorption	ISO 354:2003	Hz	125	250 500	1000 2000 4000
		αs	0,01	0,06 0,30	0,48 0,54 0,58
	ISO 11654:1997-07	αw	0,30	Hz	
Impact sound insulation	ISO 10140:2010	+/-	35	dB	
Antistatic behaviour	ISO 6356:2012	kV			
Thermal retention	ISO 8302:1991	+/-	0,128	m ² /kW	
Fire rating	EN 13501-1	Bfl-S1			

FASTNESSES

Colour fastness to light	ISO 105-B02:2013	7
Colour fastness to water	ISO 105 E01:2013	5
Rubbing fastness dry	ISO 105 X12:2002	≥ 4
Rubbing fastness wet	ISO 105 X12:2002	≥ 4



These details are approximate. Complete specification details and associated certificates together with tolerances applying to the above can be provided upon request. We reserve the right to alter specifications without notice. Due to method of manufacture, perfect pattern and/or colour matching cannot be guaranteed. In cut pile carpet, shading/pile reversal might occur without affecting overall quality and suitability. Shading/pile reversal will not be considered as a manufacturing fault and will not affect the durability of the carpet. See website for technical details broadloom and woven carpets.